




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: D01F 6/62, D02G 1/16	A1	(11) International Publication Number: WO 96/00808 (43) International Publication Date: 11 January 1996 (11.01.96)
(21) International Application Number: PCT/US95/07759 (22) International Filing Date: 19 June 1995 (19.06.95) (30) Priority Data: 08/268,585 30 June 1994 (30.06.94) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: HOWELL, James, Milton; 108 South Baywood Lane, Greenville, NC 27834 (US). TUNG, Wae-Hai; 101 Surrey Drive, Seaford, DE 19973 (US). WERNY, Frank; 334 Old Bailey Lane, West Chester, PA 19382 (US). (74) Agents: KIRVAN, George, E., Jr. et al.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CA, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: PROCESS FOR MAKING POLY(TRIMETHYLENE TEREPHTHALATE) BULKED CONTINUOUS FILAMENTS, THE FILAMENTS THEREOF AND CARPETS MADE THEREFROM

(57) Abstract

Polyester carpets of poly(trimethylene terephthalate) are disclosed which have excellent stain-resistance, texture retention and resistance to crushing. The bulked continuous filament yarn used to make the carpets and the process for making the yarns are also disclosed.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE

Process For Making Poly(trimethylene terephthalate)
Bulked Continuous Filaments, The Filaments Thereof
And Carpets Made Therefrom

5

FIELD OF THE INVENTION

This invention relates to the process for manufacturing bulked continuous filaments of poly(trimethylene terephthalate), to the resulting filaments and to carpets made from the bulked filaments.

10

BACKGROUND OF THE INVENTION

Carpets which are resistant to staining by common food dyes are currently in high demand. In order to be stain-resistant, nylon carpets must either be treated with a stain-resist chemical or the nylon fibers must have a stain-resist agent incorporated within the polymer.

15

However, carpets made from polyester fibers have the benefit of the natural stain-resistant properties of polyester. Polyester carpets are commonly made from filaments of poly(ethylene terephthalate). These carpets may have poor crush resistance (also called pile height retention) and poor texture retention (i.e., the yarns in the tuft tips unravel with wear). Carpets may develop a matted appearance in areas of high foot traffic.

20

25

Polyester carpets have also been made from filaments of poly(butylene terephthalate). While these carpets may have improved resistance to crushing vs. carpets of poly(ethylene terephthalate), the carpets may exhibit poor initial texture and poor texture retention.

30

It would therefore be useful to have a polyester carpet which has natural, built-in stain-resistance and, at the same time, adequate texture retention and resistance to crushing.

35

SUMMARY OF THE INVENTION

One embodiment of the present invention is a carpet made from bulked continuous filament (BCF) yarn of poly(trimethylene terephthalate). The carpets have built-in stain-resistance and a texture retention and resistance to crushing which is superior to that of carpets made from similar BCF yarns of poly(ethylene terephthalate) or poly(butylene terephthalate).

The carpets of this invention are tufted with crimped ply-twisted yarns made from multiple bulked continuous filaments having randomly spaced 3-dimensional curvilinear crimp, a boil off bundle crimp elongation (BCE) (as later defined herein) between 20-95 percent and a shrinkage (as later defined herein) from 0 to 5 percent. The filaments are made from poly(trimethylene terephthalate) having an intrinsic viscosity between about 0.6 to 1.3.

A second embodiment of this invention is the poly(trimethylene terephthalate) BCF yarn used to make the carpets of this invention. The bulked continuous filament yarns of this invention have an intrinsic viscosity between 0.6 to 1.3, a boil off BCE between 20 to 95 percent, a shrinkage from 0 to 5 percent, a denier per filament between 4 and 25 and a total denier between 700 and 5000. Tenacity is in the range of 1.2 to 3.5 grams per denier (gpd) and break elongation is between 10 to 90 percent, preferably 20 to 70 percent.

A third embodiment of this invention is the process for manufacturing the BCF yarn. The overall process comprises the steps of:

a) extruding molten poly(trimethylene terephthalate) polymer at a temperature between 245° C to 285° C through a spinneret to form filaments, said poly(trimethylene terephthalate) polymer having an intrinsic viscosity in the range of 0.6 to 1.3 and a water content of less than 100 ppm by weight;

b) cooling the filaments by means of air flowing perpendicularly to the filaments at a velocity in the range of 0.2 to 0.8 m/sec.;

- c) coating the filaments with a spin finish;
- d) heating the filaments to a temperature greater than the glass transition temperature of the filaments, but less than 200° C prior to drawing the filaments;
- 5 e) drawing the filaments between a set of feed rolls and a set of draw rolls to a draw ratio high enough that the break elongation of the drawn filaments is between 10 to 90%, the temperature of the draw rolls being from 120° to 200° C;
- 10 f) feeding the drawn filaments from the draw rolls at a speed of at least 800 m/min. to a bulking unit in which the filaments are blown and deformed in three dimensions with hot bulking fluid having a temperature at least as high as that of the draw rolls to form bulked continuous
- 15 filaments having randomly spaced curvilinear crimp;
- g) cooling the bulked continuous filaments to a temperature less than the glass transition temperature of the filaments; and
- h) winding up the filaments at a speed at least 10%
- 20 lower than that of the draw rolls.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic diagram of an embodiment of this invention wherein a heated feed roll is used to

25 raise the temperature of the filaments above the glass transition temperature prior to drawing.

Fig. 2 is a schematic diagram of an embodiment of this invention wherein a steam draw assist jet is used to preheat the filaments prior to drawing.

30

DETAILED DESCRIPTION OF THE INVENTION

Fig. 1 illustrates a method for manufacturing bulked continuous filaments of poly(trimethylene terephthalate). Poly(trimethylene terephthalate) polymer

35 having an intrinsic viscosity of 0.6 to 1.3, preferably 0.8 to 1.1 and a water content less than about 100 ppm is extruded at a temperature between 245° to 285° C through spinneret 10 to form filaments 12 which are pulled by feed roll 14 through quench chimney 16 where the filaments are

cooled by a radial flow or cross flow of gas, typically humidified air at a temperature between 10° to 30° C and at a velocity between 0.2-0.8 m/sec. Prior to feed rolls 14, a spin finish is applied to the filaments by finish applicator 18.

It is critical that the filaments be at a temperature above their glass transition temperature (T_g) and below 200° C prior to drawing. Non-uniform drawing and yarn breakage results when drawing below the T_g . Above 200° C is too close to the yarn melting point to effectively orient the molecules. The glass transition temperature of poly(trimethylene terephthalate filaments varies between about 35°-50° C depending upon the moisture content of the filaments, the exact polymer composition and processing conditions such as quenching. In the process shown in Fig. 1, feed rolls 14 may be heated to a temperature between the glass transition temperature and 200°C in order to heat the filaments for drawing. In an alternate embodiment, feed rolls 14 may be at room temperature and a heated draw pin (not shown), located between the feed rolls and draw rolls 22 may be used to heat the filaments to a temperature between the filament glass transition temperature and 200° C prior to drawing.

A preferred embodiment is shown in Fig. 2 where a hot fluid draw assist jet 32 is used to heat the filaments to a temperature between their glass transition temperature and 200° C. The hot fluid may be air or steam. When a steam jet is used, a large amount of finish is removed from the filaments and it is necessary to apply a post draw finish with applicator 34.

Filaments then pass over optional change of direction pin 20 and then draw rolls 22 which are maintained at a temperature between 120° to 200° C to promote annealing. The temperature must be at least about 120° C in order to heat the yarn for bulking. Heating the yarn above about 200° C may cause it to melt onto the hot rolls. The draw ratio of the filaments is controlled by adjusting the speeds of the feed rolls and/or the draw

rolls until the break elongation of the filaments is between 10 to 90 percent, preferably 20-70%. This typically corresponds to a draw ratio between about 3 to 4.5.

5 The draw rolls 22 deliver the filaments to a jet bulking unit 24 such as that described in United States Patent No. 3,525,134 (the disclosure of which is hereby incorporated by reference) where the filaments are blown and deformed in three directions with hot bulking fluid
10 such as air or steam. The hot fluid must be at a temperature of at least that of the draw rolls 22, preferably between 120° to 220° C.

 The resultant bulked continuous filament (BCF) yarn, having randomly spaced 3-dimensional curvilinear
15 crimp, is then cooled below the glass transition temperature of the filaments while the yarn is in a state of approximately 0 gpd tension so as not to pull out a significant amount of crimp. Cooling may be accomplished by a variety of commercially available means. In a
20 preferred embodiment, the BCF yarn is ejected from bulking unit 24 onto a rotating drum 26 having a perforated surface through which air is suctioned. To aid in cooling, an optional mist quench 28 of water may be used. Filaments then pass
25 over roll 30 and are wound up at a speed of at least 10% less than that of the draw rolls. The wind-up speed is kept at least about 10% less than that of the draw rolls because running at a higher speed would cause crimp development to decrease and yarn shrinkage to increase.

30 In the bulking unit described in United States Patent No. 3,525,134, the filaments are both bulked and entangled. When other bulking units are used, a separate entangling step may be necessary prior to wind up. Any method common in the trade may be used to entangle the
35 yarn.

 Combining the spinning, drawing and texturing steps into a single process as described in the preceding embodiments offers high productivity and gives a uniform,

reproducible yarn. Of course the steps described above may also be used in a split process as well.

The bulked continuous filament yarns of this invention have an intrinsic viscosity between 0.6 to 1.3, a boil off BCE between 20 to 95 percent, a shrinkage from 0 to 5 percent, a denier per filament between 4 and 25 and a total denier between 700 and 5000. Tenacity is in the range of 1.2 to 3.5 gpd and break elongation is between 10 to 90 percent, preferably 20 to 70 percent. Although these BCF yarns are particularly useful in carpets, their end uses could also include upholstery and wall covering. The yarns have excellent bending recovery (as defined in the Test Methods below) of at least 65% while BCF yarn of poly(ethylene terephthalate) has a recovery less than about 40% and BCF yarn of poly(butylene terephthalate) is less than about 60%. Bending recovery is indicative of how well a yarn can bounce back to its original geometry after a load has been removed. The higher the percent recovery, the more the yarn is able to return to its original geometry. In the case of carpet, high bending recovery implies good crush resistance (pile height retention).

In addition to their superior bending properties, the random 3-dimensional curvilinear crimp BCF yarns of the present invention are especially useful in carpets due to the nature of the crimp. These curvilinear crimped yarns have high crimp permanence. Yarns having other forms of crimp such as asymmetrically quenched helical crimp, may have a low crimp regeneration force (or crimp permanence) so that crimp is permanently pulled out during normal carpet manufacturing steps. Little curvilinear crimp is permanently pulled out of the yarns of this invention during carpet manufacture. Also, yarns having random 3-dimensional curvilinear crimp are unable to stack on top of each other. Non-randomly crimped yarns can stack on top of each other (sometimes referred to as "follow the leader"). This stacking causes there to be less bulk in the resulting carpet pile and thus more yarn is required to provide a desired cover.

Carpets made from the BCF yarns of this invention may be made in any of the manners known to those skilled in the art. Typically, a number of yarns are cable twisted together (about 3.5 to 6.5 twists per inch) and heat set (about 270° to 290° F) in a device such as an autoclave, suessen or Superba(R) and then tufted into a primary backing. Latex adhesive and a secondary backing are then applied. Cut pile style carpets having a pile height between about 0.25 to 1 inches or loop pile style carpets having a pile height between about 0.125 to 0.375 inches can be made with these BCF yarns. Typical carpet weights are between about 25 to 90 ounces per square yard.

Surprisingly, carpets of this invention have superior texture retention (as defined in the test method below) of at least 4.0 and pile height retention (as defined in the test method below) of at least 90%, preferably at least 95%, and a stain rating of at least 4.0. Carpets of similar construction and yarns except of poly(ethylene terephthalate) have texture retentions less than 3.5 and pile height retentions less than 90% with a stain rating of about 3.5. Carpets of similar construction and yarns except of poly(butylene terephthalate) have texture retention less than 2.0 and pile height retention less than 90% with a stain rating of about 4.

Test Methods

Intrinsic Viscosity

This is the viscosity of a 0.32 percent by weight solution of polyester polymer or yarn in a mixed solvent of 25 parts trifluoroacetic acid and 75 parts methylene chloride (volume/volume) measured in an Ostwald-Cannon-Fenske series 50 viscometer at 25° C.

Boil Off Bundle Crimp Elongation (BCE)

Bundle crimp elongation (BCE) is the amount a boiled-off, conditioned yarn sample extends under 0.10 grams/denier tension, expressed as percent of the sample length without tension. In the boil-off procedure, a yarn

sample length of about 1 meter is coiled in a relaxed condition into a 10 cm diameter perforated can, and then immersed for three minutes in rapidly boiling water at 100° C. The sample and can are then removed from the water and dipped into and out of room temperature water to cool the sample. The sample is then centrifuged to remove excess water, dried in a hot-air oven at 100° to 110° C for one hour and then conditioned for at least an hour prior to measurement of BCE.

10 A 50 cm. length (L1) of the test sample in a relaxed condition is mounted in a vertical position. The sample is then extended by gently hanging a weight on the yarn to produce a tension of 0.10 ± 0.02 gram/denier. The extended length (L2) is read after the tension has been applied for at least three minutes. BCE, in percent, is then calculated as $100(L2-L1)/L1$. Results are normally reported as averages of three tests per sample.

Shrinkage

20 Shrinkage is the change in extended length of yarn or fiber which occurs when the yarn or fiber is treated in a relaxed condition in boiling water at 100° C. To determine continuous filament yarn shrinkage, a piece of conditioned yarn sample is tied to form a loop of between 65 and 75 cm length. The loop is hung on a hook on a meter board and a 125-gram weight is suspended from the other end of the loop. The length of the loop is measured to give the before boil-off length (L1). The weight is then removed from the loop. The sample is loosely wrapped in an open-weave cloth (e.g., cheese cloth), placed in 100° C boiling water for 20 minutes, removed from the water, centrifuged, removed from the cloth and allowed to hang-dry at room conditions prior to undergoing the usual conditioning before further measurement. The dried, conditioned loop is then rehung on the meter board, the 125-gram weight is replaced, and the length of the loop measured as before to give the after boil-off length (L2). The yarn shrinkage, expressed as a percent, is then calculated as $100(L1-L2)/L1$, and as

reported herein is the average of three such measurements for a given yarn.

Bending Recovery

5 This test provides information on the recovery property of fiber. The technique used is described by Prevorsek, Butler and Lamb (Tex. Res. J. February, 1975, PP. 60-67). In this test, the yarn is hung over a wire of
10 of the yarn for 60 seconds. The test is performed at 24° C and at 57% relative humidity (RH). The filament is then removed and the amount of "recovery" is immediately measured. A value of 0 degrees would be no recovery. A value of 180 degrees corresponds to complete recovery.

15

Staining Test

 A sample approximately 6 inches by 6 inches is cut from a carpet. A staining agent of hot (about 50° C) coffee is used. The carpet sample is placed on a flat,
20 non-absorbent surface; 20 ml of the coffee staining agent is poured onto the sample from a height of 12 inches above the carpet surface and the sample is then left undisturbed for 24 hours. To confine the stain, a cylinder of
25 carpet and the staining agent may be poured through it.

 Excess stain is blotted with a clean white cloth or clean white paper towel or scooped up as much as possible. Blotting is always performed from the outer edge of the spill towards the middle to keep the spill
30 from spreading. Cold water is applied with a clean white cloth or a sponge over the stained area, gently rubbing against the pile from left to right and then reversing the direction from right to left. The excess is blotted.

 A detergent cleaning solution (15 g of TIDE
35 detergent mixed in 1000 ml of water and allowed to reach room temperature prior to use) is applied with a clean white cloth or sponge directly on the stain, gently rubbing the pile from left to right and then reversing direction from right to left. The entire stain is treated

all the way to the bottom of the pile and then the blotting is repeated.

The cold water treatment is repeated, and the carpet is blotted thoroughly to remove the stain and the cleaning solution.

The cold water and detergent cleaning steps are repeated until the stain is no longer visible or until no further progress in removing the stain can be achieved. The carpet is blotted completely to absorb all the moisture.

The stain resistance of the carpet is visually determined by the amount of color left in the stained area of the carpet after this cleaning treatment. The scale used is

5=no staining
4=slight staining
3=noticeable staining
2=considerable staining
1=heavy staining.

20

Texture Retention

The texture retention data are obtained by subjecting the test carpets to 11,000 cycles of human traffics and visually determining a rating based on the degree of matting versus a set of control samples. The texture retention is reported on a scale of 1 to 5 with a rating of 5 corresponding to an untested control sample, 4 corresponding to a lightly worn sample, 3 to a moderately worn sample, 2.5 to the turning point from acceptable to unacceptable wear, 2 corresponding to clearly unacceptable wear, and 1 corresponding to an extremely matted sample.

30

Pile Height Retention

The percent pile height retention is 100 times the ratio of the pile height of carpet tufts after 11,000 traffics to the pile height of the carpet tufts before traffics.

35

EXAMPLES

Example 1

Poly(trimethylene terephthalate) polymer having
5 an intrinsic viscosity of 0.90 and less than 50 ppm
moisture was spun through a 160 hole spinneret into two
segments, each of 80 filaments having a trilobal cross
section with a modification ratio (MR) of 1.7. The
polymer temperature before the spinning pack was
10 controlled at about $260^{\circ}\pm 1^{\circ}$ C and spinning throughput was
335 grams per minute. The molten filaments were then
rapidly quenched in a chimney, where cooling air at 10° C
was blown past the filaments at 300 cubic ft./min (0.236
cubic m/sec). The filaments were pulled by an unheated
15 feed roll rotating at a surface speed of 630 yd./min
through the quench zone and then were coated with a
lubricant for drawing and crimping. The coated yarns were
passed through a steam draw jet, a post draw jet finish
applicator and onto a pair of heated draw rolls which
20 rotated at 2177 yd./min (3.45 X draw ratio). The
temperature in the draw jet was 200° C and the draw roll
temperature was 180° C. The yarns were then forwarded into
a dual-impingement bulking jet (195° C hot air), similar
to that described in Coon, U.S. Patent No. 3,525,134, to
25 form two 1200 denier, 15 denier per filament (dpf) bulked
continuous filament yarns. Yarns had a shrinkage=2.44%,
tenacity=2.08 grams per denier (gpd), elongation=20.5%,
modulus=53.68 gpd and a boil off BCE=57.6%.

Before determining bending recovery, the yarns
30 were ply twisted (4x4) and heatset in an autoclave at
 280° F. Bending recovery data are shown on Table I.

Example 2 (comparative)

A commercial grade poly(ethylene terephthalate)
35 polymer, code 1914F available from Du Pont, was spun into
1200 denier, 15 dpf, 1.7 MR trilobal cross section yarn
using the process described in Example 1 except that no
post draw jet finish application was necessary. The
spinning (290° C), draw roll (190° C) and bulking jet

(220° C) temperatures were also higher than in Example 1 due to the higher melting temperature of poly(ethylene terephthalate) versus that of poly(trimethylene terephthalate). The yarn had a shrinkage=4.11%,
5 tenacity=3.63 gpd, elongation=27.8%, modulus=45.90 gpd and a boil off BCE=66.3%.

Bending recovery data for the ply twisted, heatset yarns are shown in Table I.

10 Example 3 (comparative)

A commercial grade poly(butylene terephthalate) polymer, RYNITE 6131 available from DuPont, was spun into 1200 denier, 15 dpf, 1.7 MR trilobal cross section yarn using the process described in Example 1 except without
15 the steam heated draw assist jet and post draw jet finish application. The spinning temperature was slightly lower (247° C) due to the lower polymer melting temperature. Yarn had a shrinkage=3.04%, tenacity=2.79 gpd, elongation=12.8, modulus=43.07 gpd, and a boil off
20 BCE=74.6%

Bending recovery data for the ply-twisted heatset yarns are shown in Table I.

Table I

25	<u>Sample</u>	<u>Recovery</u>
	Example 1	119.4
	Example 2	71.3
	Example 3	107.9

30 The data in Table I show that the poly(trimethylene terephthalate) BCF yarns of Example 1 have greater bending recovery than the yarns of Example 2 [poly(ethylene terephthalate)] or Example 3 [poly(butylene terephthalate)]. Therefore, the yarns of Example 1 should
35 have better pile height retention (crush resistance) in carpets.

Example 4

The test yarns produced in Examples 1, 2 and 3 were cable twisted 4 x 4 twist per inch, autoclave heatset at 280° F and tufted into 5/8 inch pile height, 40 oz. per square yard cut pile carpets on a 1/8 inch gauge tufting machine. The carpets were Beck dyed in medium blue color with disperse dyes. The carpets made from yarns of Examples 1 and 2 had good pin point tuft definition. Carpet made from yarns of Example 3 had very poor tuft definition. It looked like a felt instead of saxony carpet. The texture retention, pile height retention and staining test results are shown in Table II.

15

Table II

<u>Carpets Yarn</u>	<u>Texture Rating</u>	<u>Pile Height Retention</u>	<u>Stain Rating</u>
Example 1	4.0	97%	4.5
20 Example 2	3.4	89%	3.5
Example 3	2.0	89%	4.0

Surprisingly, carpets made from the poly(trimethylene terephthalate) BCF yarns of Example 1 have significantly better texture retention and pile height retention than carpets of either poly(ethylene terephthalate) (Example 2) or poly(butylene terephthalate) (Example 3) yarns.

We claim:

1. A process for the production of poly(trimethylene terephthalate) bulked continuous filaments comprising the steps of:

- 5 a) extruding molten poly(trimethylene terephthalate) polymer at a temperature from 245° C to 285° C through a spinneret to form filaments, said poly(trimethylene terephthalate) polymer having an intrinsic viscosity in the range of 0.6 to 1.3 and a water
10 content of less than 100 ppm by weight;
- b) cooling the filaments in a quench chimney by means of air flowing perpendicularly to the filaments at a velocity in the range of 0.2 to 0.8 m/sec.;
- c) coating the filaments with a spin
15 finish;
- d) heating the filaments to a temperature greater than the glass transition temperature of the filaments, but less than 200° C prior to drawing the filaments;
- 20 e) drawing the filaments between a set of feed rolls and a set of draw rolls to a draw ratio high enough that the break elongation of the drawn filaments is between 10 to 90%, the temperature of the draw rolls being from 120° to 200° C;
- 25 f) feeding the drawn filaments from the draw rolls at a speed of at least 800 m/min. to a bulking unit in which the filaments are blown and deformed in three dimensions with hot bulking fluid having a temperature at least as high as that of the draw rolls to
30 form bulked continuous filaments having randomly spaced curvilinear crimp;
- g) cooling the bulked continuous filaments to a temperature less than the glass transition temperature of the filaments;
- 35 h) winding up the filaments at a speed at least 10% lower than that of the draw rolls.

2. The process of claim 1 wherein the filaments are heated for drawing by a heating means located between the feed rolls and the draw rolls and wherein the

temperature of the feed rolls is less than the glass transition temperature of the filaments.

3. The process of claim 2 wherein said heating means is a hot fluid jet.

5 4. The process of claim 3 wherein the hot fluid is steam and further comprising the step of coating the drawn filaments with a post draw finish prior to feeding the drawn filaments to a bulking unit.

10 5. The process of claim 2 wherein said heating means is a heated draw pin.

15 6. The process of claim 1 wherein the filaments are heated for drawing by setting the temperature of the feed rolls to a temperature greater than the glass transition temperature of the filaments, but less than 200° C.

7. The process of claim 1 wherein the filaments are drawn to a draw ratio high enough that the break elongation of the filaments is between 20 to 70%.

20 8. The process of claim 1 wherein the temperature of the bulking fluid is between 120° to 220° C.

25 9. The process of claim 1 wherein prior to wind up the bulked continuous filaments are cooled below the filament glass transition temperature on a rotating drum having a perforated surface through which air is suctioned.

30 10. The process of claim 1 further comprising the step of entangling the bulked continuous filaments after the filaments have been cooled below their glass transition temperature and prior to wind up.

35 11. A yarn comprising a plurality of bulked continuous filaments having randomly spaced 3-dimensional curvilinear crimp, wherein said filaments are of poly(trimethylene terephthalate) having an intrinsic viscosity between 0.6 and 1.3 and wherein said filaments have a total denier between 700 and 5000, a denier per filament between 4 and 25, a boil off BCE between 20 and 95% and a shrinkage from 0 to 5 percent.

12. The yarn of claim 11, wherein said filaments have a tenacity between 1.2 and 3.5 gpd.

13. The yarn of claim 12, wherein said filaments have a break elongation between 10 and 90 percent.

5 14. The yarn of claim 13, wherein said filaments have a break elongation between 20 and 70 percent.

15. A carpet comprising tufts of crimped ply-twisted yarns, said yarns containing multiple bulked continuous filaments having randomly spaced 3-dimensional curvilinear crimp, wherein said filaments are of poly(trimethylene terephthalate) having an intrinsic viscosity between about 0.6 and 1.3, a boil off BCE between 20-95% and a shrinkage from 0 to 5 percent.

16. The carpet of claim 15, wherein said yarn has a denier between about 700 and about 5000.

17. The carpet of claim 16, wherein said filaments have a denier per filament of about 4 to about 25.

18. The carpet of claim 17, wherein said yarn has a ply twist level between about 3.5 to about 6.5 turns per inch.

19. The carpet of claim 18, wherein said carpet has a weight between about 25 to about 90 oz./sq. yd.

20. The carpet of claim 19, wherein said carpet is a cut pile style carpet having a pile height from 0.25 to 1 inch.

21. The carpet of claim 20 wherein said carpet is a loop pile style carpet having a pile height from 0.125 to 0.375 inches.

30




FIG. 1




FIG. 2

INTERNATIONAL SEARCH REPORT

Internat. Application No
PCT/US 95/07759A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D01F6/62 D02G1/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 D01F D02G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A P,A	EP,A,0 350 626 (ZIMMER AG) 17 January 1990 --- CHEMICAL FIBERS INTERNATIONAL, vol. 45, no. 2, April 1995 FRANKFURT/MAIN, DE, pages 110-111, H.L. TRAUB ET AL. 'Mechanical properties of fibers made of polytrimethylene terephthalate' ---	
A	EP,A,0 547 553 (HOECHST CELANESE CORP) 23 June 1993 ---	
A	US,A,3 681 188 (HARRIS MAX EMERSON) 1 August 1972 ---	
	--- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 October 1995

Date of mailing of the international search report

24 -10- 1995

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Tarrida Torrell, J

INTERNATIONAL SEARCH REPORT

Intern. J Application No
PCT/US 95/07759

C(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 7709 Derwent Publications Ltd., London, GB; Class A23, AN 77-15710Y & JP,A,52 008 124 (TEIJIN KK) , 21 January 1977 see abstract</p> <p>----</p>	
A	<p>DATABASE WPI Section Ch, Week 7709 Derwent Publications Ltd., London, GB; Class A23, AN 77-15709Y & JP,A,52 008 123 (TEIJIN KK) , 21 January 1977 see abstract</p> <p>----</p>	
A	<p>DATABASE WPI Section Ch, Week 7709 Derwent Publications Ltd., London, GB; Class A23, AN 77-15131Y & JP,A,52 005 320 (TEIJIN KK) , 17 January 1977 see abstract</p> <p>----</p>	
A	<p>GB,A,578 079 (JOHN REX WHINFIELD ET AL.) 11 July 1946</p> <p>-----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat'l Application No

PCT/US 95/07759

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0350626	17-01-90	DE-A- 3823538 DE-D- 58905436 US-A- 4877572	01-02-90 07-10-93 31-10-89
EP-A-0547553	23-06-93	US-A- 5340909 JP-A- 5262862	23-08-94 12-10-93
US-A-3681188	01-08-72	NONE	
GB-A-578079		NONE	